

PolyPropylene

Commercial Product List

Product Name	MFR ⁽¹⁾	Flex. Mod. (MPa)	Charpy Impact ⁽²⁾ (23°C)	Charpy Impact ⁽²⁾ (0°C)	Charpy Impact ⁽²⁾ (-20°C)	Properties	Processes/Applications
Impact Copolymers							
Safron® C790-90RNA	90	1050	6.0	5.0	4.2	Nucleated, antistatic	Injection moulding - Food containers, yoghurt cups, margarine tubs, housewares, lids, caps & closures
Safron® C740-25RNA	25	900	10	7	5.5	Nucleated, antistatic	Injection moulding - Ice-cream containers, frozen food containers
Safron® C765-15NA	15	1200	12	~	6.5	Nucleated, antistatic	Injection moulding - Crates, boxes, toys, pails, household appliances
Safron® C722-07NA	7.5	1250	10.5	5.5	~	Nucleated, antistatic	Injection moulding - Houseware, appliances, battery cases and containers
Safron® C142-01N	1.4	1200	~	7	5	Nucleated	Extrusion & injection moulding - Thin walled sheet and profile extrusion
Random Copolymers							
Advance 400®	40	1000	5	2	~	Nucleated, antistatic	Injection moulding - Thin wall packaging, food and cosmetic containers, aerosol dust covers
Advance 150®	1.5	1000	11	3	~	Nucleated, UV stabilized	Extrusion, blow moulding & thermoforming - Toiletry containers, petroleum jelly jars, high clarity bottles, film for retort applications
Homopolymers							
Safron® H712-52RNM	50	1500	2.3	~	~	Nucleated	Injection moulding & extrusion coating - Thin walled food and cosmetic packaging, houseware & appliances, caps & closures
Safron® H500-25RG	26	1370	3.0	~	~	Anti-gas fading	Extrusion fibre spinning - Health & hygiene products, geotextiles, carpet face yarns
Safron® H504-12M	12	1360	2.3	~	~		Extrusion and injection moulding - High tenacity yarns, fibres, tufted carpets
Safron® H707-12NSM	12	1500	2.3	~	~	Nucleated, slip	Injection moulding - Houseware & appliances, garden furniture, caps & closures
Safron® H713-06	5.4	1450	4.5	~	~		Injection moulding - Caps and closures, domestic ware, slit tapes for woven bags
Safron® H511-03	3.3	1350	5.8	~	~		Extrusion - Slit film tapes, tapes and monofilaments, ropes and twines
Safron® H510-02	2.0	1360	6.8	~	~		Extrusion, injection & blow moulding - Hinged closures, monofilaments, strapping
Safron® H106-02NSA	2.0	1480	6.0	2.2	~	Nucleated, slip, antistatic	Extrusion & compression moulding - Carbonated soft drink closures

⁽¹⁾ MFR = g/10min, 2,16kg @ 230°C

⁽²⁾ Charpy Impact (kJ/m²) notched

NOTICE: No freedom from infringement of any patent owned by Safripol (Pty) Ltd or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, the Customer is responsible for determining whether products and the information in this document are appropriate for the Customer's use and for ensuring that the Customer's workplace and disposal practices are in compliance with applicable laws and other governmental enactments. It is also the responsibility of both the manufacturers of finished food contact articles as well as the industrial food packers to ensure that these articles in their actual use are in compliance with the imposed food contact regulations. For any further information on product stewardship kindly contact info@safripol.com

SAFRIPOL MEDICAL APPLICATION POLICY: Safripol does not endorse or claim suitability of their products for specific medical applications. It is the responsibility of the medical device or pharmaceutical manufacturer to determine that the Safripol product is safe, lawful, and technically suitable for the intended use. SAFRIPOL MAKES NO WARRANTIES, EXPRESS OR IMPLIED, CONCERNING THE SUITABILITY OF ANY SAFRIPOL PRODUCT FOR USE IN MEDICAL APPLICATIONS.

Safripol assumes no obligation or liability for the information in this document. **NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.**

Contact Details:	Gauteng	Tel: +27 (0) 11 575 4549	Kwa-Zulu Natal	Tel: +27 (0) 31 4504111
	Website:	www.safripol.com	Email:	info@safripol.com