

# Safrene<sup>®</sup> (High Density PolyEthylene)

## Technical Data Sheet

### F 7740F3

#### High-Density Polyethylene for Extrusion Applications

Safrene<sup>®</sup> F 7740F3 Density Polyethylene Resin is a medium molecular mass extrusion grade ideally suited to the extrusion and subsequent knitting of tapes and monofilaments typically used in agricultural pockets and shade netting.

Safrene<sup>®</sup> F 7740F3 Density Polyethylene Resin is also used for film extrusion applications where excellent roll geometry is required. As a film it exhibits an excellent barrier to moisture.

#### Typical Applications

- Monofilaments
- Stretched tapes
- Films for laminating
- Co-extruded films
- Drip-bag over pouches

PROPERTIES <sup>(1)</sup>	VALUE	UNIT	TEST METHOD
<b>Physical</b>			
Melt Flow Rate, 190 °C/ 5 kg	1.5	g/10min	ISO 1133
Density <sup>(2)</sup>	0.947	g/cm <sup>3</sup>	ISO 1183
<b>Mechanical<sup>(3)</sup></b>			
Tensile Yield <sup>(4)</sup>	21	MPa	ISO 527
Ultimate Tensile <sup>(4)</sup>	33	MPa	ISO 527
Ultimate Elongation <sup>(4)</sup>	>600	%	ISO 527
<b>Thermal</b>			
Crystalline Melting Range	130 - 133	°C	ISO 3146-85

(1) Typical values; not to be construed as specification limits.

(2) Unannealed.

(3) Compression moulded samples.

(4) Test speed 50mm/min.

Typical Processing Conditions	Extrusion
Feed Zone (°C)	170
Die (°C)	230 - 260
Melt Temp (°C)	210 - 240

# Safrene® (High Density PolyEthylene)

## Technical Data Sheet

**F 7740F3**

### High-Density Polyethylene for Extrusion Applications

<p><b>Product Stewardship</b></p>	<p>At Safripol, protecting people and the environment will be a part of everything we do and every decision we make. Each employee has a primary responsibility in ensuring that our products and operations meet applicable government standards. Our goal is to eliminate all injuries, prevent adverse environment and health impacts, reduce wastes and emissions and promote resource conservation at every stage of the life cycle of our products. The success of this rests with each and every individual involved with Safripol products throughout the life cycle.</p>
<p><b>Food Contact Compliance</b></p>	<p>Safrene® F 7740F3 High Density Polyethylene Resin should comply with Commission Regulation (EU) No 10/2011 and with U.S. FDA 21 CFR 177.1520(c)3.2a food contact regulations when used unmodified and processed according to good manufacturing practices for food contact applications. The purchaser remains responsible for determining whether the use complies with all relevant regulations.</p>
<p><b>Customer Notice</b></p>	<p>Safripol strongly encourages its customers to review both their manufacturing processes and their applications of Safripol products from the standpoint of human health and environmental quality to ensure that Safripol products are not used in ways for which they are not intended or tested. Safripol personnel are available to answer your questions and to provide reasonable technical support. Safripol product literature, including safety data sheets, should be consulted prior to use of Safripol products. Current safety data sheets are available from Safripol.</p>
<p><b>Safripol Medical Application Policy</b></p>	<p>Safripol will not knowingly sell or sample any product or service ("Product") into any commercial or developmental application that is intended for:</p> <ol style="list-style-type: none"> <li>permanent (Long term) contact with internal body fluids or internal body tissues. Long term is a use which exceeds 72 continuous hours.</li> <li>use in cardiac prosthetic devices regardless of the length of time involved; (Cardiac prosthetic devices include, but are not limited to, pacemaker leads and devices, artificial hearts, heart valves, intra-aortic balloons and control systems, and ventricular bypass assisted devices);</li> <li>use as a critical component in medical devices that support or sustain human life; or</li> <li>use specifically by pregnant women or in applications designed specifically to promote or interfere with human reproduction.</li> </ol> <p>Additionally, all Products intended for use in pharmaceutical applications, other than pharmaceutical packaging, must pass the current Pharmaceutical Liability Guidelines.</p> <ul style="list-style-type: none"> <li>New business opportunities require a business assessment prior to sale or sampling of Safripol products.</li> <li>Authorized distributors and resellers will adhere to this medical policy.</li> <li>Safripol does not endorse or claim suitability of their products for specific medical applications. It is the responsibility of the medical device or pharmaceutical manufacturer to determine that the Safripol product is safe, lawful, and technically suitable for the intended use.</li> </ul> <p><b>SAFRIPOL MAKES NO WARRANTIES, EXPRESS OR IMPLIED, CONCERNING THE SUITABILITY OF ANY SAFRIPOL PRODUCT FOR USE IN MEDICAL APPLICATIONS.</b></p>
<p><b>Disclaimer</b></p>	<p>The Customer is responsible for determining whether products and the information in this document are appropriate for the Customer's use and for ensuring that the Customer's workplace and disposal/ recycling practices of our products and packaging are in compliance with applicable laws and other governmental enactments. Safripol assumes no obligation or liability for the information in this document.</p> <p><b>NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.</b></p> <p>NOTICE: If products are described as "experimental" or "developmental": (1) product specifications may not be fully determined; (2) analysis of hazards and caution in handling and use are required; and (3) there is greater potential for Safripol to change specifications and/or discontinue production</p>
<p><b>Additional Information</b></p>	
<p>Our contact details:</p> <p>Safripol (Pty) Ltd PrivateBag X 52 Bryanston 2021 South Africa</p> <p>Website: <a href="http://www.safripol.com">www.safripol.com</a></p> <p>Published:</p>	<p><b>Gauteng:</b> Tel: +27 (0) 11 575 4549</p> <p><b>Kwa-Zulu Natal:</b> Tel: +27 (0) 450 4111</p> <p>Email: <a href="mailto:info@safripol.com">info@safripol.com</a></p> <p>January 2022</p>